



Technical Datasheet

PETG

Version: 1.0

Date: 07.08.2026

MATERIAL PETG	MANUFACTURER Recycling Fabrik GmbH
BRAND Everloop	COUNTRY OF MANUFACTURE Germany

1. PRODUCT DESCRIPTION

Everloop PETG is a high-quality 3D printing filament manufactured from recycled plastics. It is engineered to provide excellent printability, strong interlayer adhesion, and proper impact resistance. The material combines ease of processing with durability, making it suitable for functional parts, prototypes, and end-use applications.

2. MATERIAL INFORMATION

- **Polymer:** Polyethylene Terephthalate Glycol (PETG)
- **Feedstock:** Recycled post-industrial plastic
- **Additives:** Color masterbatch, stabilizers (if applicable)
- **Technology:** Recycling Fabrik industrial recycling system

3. MECHANICAL PROPERTIES

PROPERTY	VALUE	UNIT	STANDARD
Tensile Strength	45-50	MPa	ISO 527
Young's Modulus	1800-2000	MPa	ISO 527
Elongation at Break	10-20	%	ISO 527
Impact Strength	4-6	kJ/m ²	ISO 180

4. THERMAL PROPERTIES

PROPERTY	VALUE	UNIT	STANDARD
Glass Transition Temperature	~75-80	°C	DSC
Vicat Softening Temperature	~75-85	°C	ISO 306
Recommended Processing Temp.	230-260	°C	–

5. PRINTING PARAMETERS

- **Nozzle Temperature:** 230 – 260 °C
- **Bed Temperature:** 70 – 80 °C
- **Print Speed:** 40 – 120 mm/s
- **Cooling Fan:** 0 – 50 %
- **Nozzle Diameter:** ≥ 0.4 mm

Note: Settings may vary depending on printer, geometry, and color.

6. PHYSICAL PROPERTIES

PROPERTY	VALUE	UNIT	STANDARD
Density	~1,275	g/cm ³	–
Diameter	1.75 mm ± 0.05	mm	–
Ovality	≤ 0.05	mm	–

7. OTHER INFORMATION

- **Surface finish:** glossy to semi-matte
- Constant and reliable Colors
- **Drying recommended:** 50 °C for 4–6 hours
- PETG is hygroscopic → moisture may cause stringing or bubbles
- Good adhesion on PEI, glass, and coated build plates
- Store in a cool, dry, UV-protected environment
- **Recommended humidity:** < 50% RH
- Keep in packaging when not in use

8. SUSTAINABILITY

- Reduced carbon footprint compared to virgin materials
- Produced from recycled plastics in Germany
- Compatible with Recycling Fabrik circular system

9. DISCLAIMER

All data provided are typical values and do not constitute a specification. Users must verify suitability for their specific application.